



(11) **EP 0 820 301 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
**24.07.2002 Bulletin 2002/30**

(51) Int Cl.7: **A61L 27/00, A61K 35/38**

(86) International application number:  
**PCT/US96/04590**

(21) Application number: **96911561.7**

(87) International publication number:  
**WO 96/31232 (10.10.1996 Gazette 1996/45)**

(22) Date of filing: **03.04.1996**

(54) **TISSUE GRAFT FOR URINARY BLADDER RECONSTRUCTION**

**GEWEBETRANSPLANTAT ZUR BLASENREKONSTRUKTION**

**GREFFE DE TISSUS DE RECONSTITUTION DE VESSIE**

(84) Designated Contracting States:  
**BE DE DK ES FR GB IE IT NL SE**

(74) Representative: **Bannerman, David Gardner et al**  
**Withers & Rogers,**  
**Goldings House,**  
**2 Hays Lane**  
**London SE1 2HW (GB)**

(30) Priority: **07.04.1995 US 418516**

(56) References cited:  
**WO-A-93/05798 WO-A-93/07913**  
**US-A- 4 902 508 US-A- 5 275 826**  
**US-A- 5 352 463**

(43) Date of publication of application:  
**28.01.1998 Bulletin 1998/05**

(73) Proprietors:  

- **PURDUE RESEARCH FOUNDATION**  
**West Lafayette, IN 47907-1021 (US)**
- **Methodist Health Group, Inc.**  
**Indianapolis, IN 46206-1367 (US)**

- **KNAPP P.M. ET AL.: "BIOCOMPATIBILITY OF SMALL-INTESTINAL SUBMUCOSA IN URINARY TRACT AS AUGMENTATION CYSTOPLASTY GRAFT AND INJECTABLE SUSPENSION" JOURNAL OF ENDOUROLOGY, vol. 8, no. 2, 12 April 1994, pages 125-130, XP002059073**
- **KROPP B.P. ET AL.: "EXPERIMENTAL ASSESSMENT OF SMALL INTESTINAL SUBMUCOSA AS A BLADDER WALL SUBSTITUTE" UROLOGY, vol. 46, no. 3, September 1995, pages 396-400, XP002059074**

(72) Inventors:  

- **KNAPP, Peter, M., Jr.**  
**Carmel, IN 46032 (US)**
- **LINGEMAN, James, E.**  
**Indianapolis, IN 46278 (US)**
- **DEMETER, Robert, J.**  
**Mooreville, IN 46158 (US)**
- **BADYLAK, Stephen, F.**  
**West Lafayette, IN 47906 (US)**

**EP 0 820 301 B1**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

1

EP 0 820 301 B1

2

## Description

### Field of the Invention

[0001] The present invention relates to a tissue graft for repairing damaged or diseased urinary bladder.

### Background and Summary of the Invention

[0002] Urologists have long been searching for an alloplastic or biodegradable material suitable for use as a urinary bladder replacement graft. Many experiments have been conducted utilizing synthetic biomaterials such as silicone rubber, polytetrafluoroethylene and polypropylene for bladder reconstruction. Such materials have been found generally to induce foreign body-type reactions resulting in the rejection or mineralization of the graft.

[0003] The reported failures of experiments with synthetic biomaterials, have led researchers to investigate the use of natural or synthetic biodegradable materials, such as gastrointestinal, placental, amniotic and pericardial tissues and synthetic resorbable polymers, for bladder regeneration. These materials serve as a scaffold for endogenous cell growth, but dissolve prior to the onset of any foreign body-type reactions. In particular gastrointestinal tissue has been a preferred source of material for bladder reconstruction. However, the use of gastrointestinal tissue in bladder reconstruction has been associated with deleterious side effects such as infection, intestinal obstruction, mucus production, electrolyte abnormalities and carcinogenicity.

[0004] Placental, amniotic and pericardial tissue grafts are useful as graft materials for replacing urinary bladder tissue however, such graft materials suffer the disadvantage of graft shrinkage, and they fail to promote complete bladder wall regeneration (tissue having a urine impermeable layer and a functional muscle cell layer).

[0005] Clearly a tissue graft material is desired which is non-immunogenic, which is not subject to gross shrinkage after implantation, and which promotes the growth of endogenous urinary bladder tissues having a urine impermeable cell layer and a functional muscle cell layer.

[0006] The present invention is directed to the use of vertebrate submucosa matrices for promoting the replacement of damaged or diseased portions of a urinary bladder with endogenous urinary bladder tissue. The collagenous submucosa tissue used in accordance with the present invention comprise highly conserved collagens, glycoproteins, proteoglycans, and glycosaminoglycans in their natural configuration and natural concentration. Submucosal tissue can be obtained from various sources, including particularly intestinal tissue harvested from animals raised for meat production, including, for example, pigs, cattle and sheep or other warm-blooded vertebrates. This tissue can be used in

either its natural configuration or in a comminuted or partially digested fluidized form. Vertebrate submucosal tissue is a plentiful by-product of commercial meat production operations and is thus a low cost tissue graft material, especially when the submucosal tissue is used in its native sheet configuration.

[0007] It is known that compositions comprising the tunica submucosa and the basilar portions of the tunica mucosa of the intestine of warm-blooded vertebrates can be used as tissue graft materials in sheet form. See U.S. Patent No. 4,902,508. The compositions described and claimed in that patent are characterized by excellent mechanical properties, including high compliance, a high burst pressure point, and an effective porosity index which allowed such compositions to be used beneficially for vascular graft constructs. The graft materials disclosed in that patent are also useful in tendon, ligament and other connective tissue replacement applications. When used in such applications the preferred graft constructs appear to serve as a matrix for the regrowth of the tissues replaced by the graft constructs. Intestinal submucosal tissue has undergone extensive immunologic testing in over 600 cross-species implants and has never been shown to elicit a rejection reaction.

[0008] Furthermore, it is known that intestinal submucosa can be fluidized by comminuting and/or protease digestion, without loss of its apparent biotropic properties, for use in less invasive methods of administration (e.g., injection or topical) to host tissues in need of repair. See U.S. Patent No. 5,275,826. Fluidized comminuted intestinal tissue comprising tunica submucosa has previously been successfully used to repair and functionally augment damaged tissues including, for example, urinary bladder sphincter. Common events to tissue remodeling include widespread and rapid neovascularization, proliferation of granulation mesenchymal cells, biodegradation of implanted submucosal tissue, and lack of immune rejection.

[0009] Small intestinal submucosa has been explored as a patch graft for bladder augmentation in pigs and has been found a promising material (Knapp et al, Journal of Endourology, 1994; vol. 8(2), p.125-130).

[0010] The present invention is directed to the use of vertebrate-derived submucosal matrices as a urinary bladder graft. Submucosal tissue is an inexpensive, nonimmunogenic material that induces host tissue proliferation, remodeling and regeneration of urinary bladder tissues upon implantation. In accordance with this invention tissue graft constructs comprising submucosal tissue of a warm-blooded vertebrate have been found to promote the growth of endogenous urinary bladder tissues having both a urine impermeable cell layer and a function muscle cell layer.

### Detailed Description of the Invention

[0011] There is provided in accordance with the present invention a composition for replacing damaged

or diseased urinary bladder tissues. The submucosal graft compositions of the present invention function as a biotropic/biodegradable scaffold that induces endogenous tissues to invade and replace the graft material with endogenous urinary bladder tissue.

[0012] The submucosal tissue of the present tissue graft constructs is derived from vertebrate submucosa and comprises naturally associated extracellular matrix proteins, glycoproteins and other factors. In one embodiment the submucosal tissue comprises intestinal submucosal tissue of a warm-blooded vertebrate. The small intestine of warm-blooded vertebrates is a preferred source of submucosal tissue for use in this invention.

[0013] Intestinal-derived submucosal tissue for use in this invention comprises the tunica submucosa delaminated from both the tunica muscularis and at least the luminal portion of the tunica mucosa. In one embodiment of the present invention the intestinal submucosal tissue comprises the tunica submucosa and a basilar portion of the tunica mucosa, which can include the lamina muscularis mucosa and the stratum compactum which layers are known to vary in thickness and in definition dependent on the source vertebrate species.

[0014] The preparation of submucosal tissue for use in accordance with this invention is described in U.S. Patent No. 4,902,508. A segment of vertebrate intestine, preferably harvested from porcine, ovine or bovine species, but not excluding other species, is subjected to abrasion using a longitudinal wiping motion to remove the outer layers, comprising smooth muscle tissues, and the innermost layer, *i.e.*, the luminal portion of the tunica mucosa. The submucosal tissue is rinsed with saline and optionally sterilized; it can be stored in a hydrated or dehydrated state. Lyophilized or air dried submucosa tissue can be rehydrated, optionally stretched, and used in accordance with this invention without significant loss of its cell proliferative activity.

[0015] In one embodiment in accordance with the present invention, several strips of submucosal tissue can be adhered to one another to form a large area, submucosal sheet. The process of forming large area submucosal sheets involves cutting strips of submucosal tissue and overlapping at least a portion of each strip with a portion of an adjacent strip. The overlapped portions are then compressed under dehydrating conditions to form a large sheet of submucosal tissue. In one embodiment the strips of submucosal tissue are layered onto a permeable surface and a second optionally permeable surface is used to compress the overlapped portions between the two surfaces.

[0016] In one embodiment a tissue graft construct is formed from 2 or more strips of submucosal tissue of a warm blooded vertebrate, the graft construct having a surface area greater than any one of the individual strips.

[0017] Optionally the large area sheet of submucosal tissue can be formed from multiple layers of submucosal tissue strips. In one embodiment submucosal tissue

strips are organized on a mesh in one direction with at least a portion of one strip of submucosal tissue overlapping with at least a portion of another strip of submucosal tissue. Once the mesh is covered with one layer of submucosal tissue the second layer of submucosal tissue is applied on top of the first layer but at a different angle relative to the first layer. Additional layers of submucosal tissue can be added to obtain a graft construct having a desired strength or thickness. After all the strips of submucosal tissue are placed on the mesh, another mesh is placed on top of the submucosal tissues and the "mesh-submucosal tissue-mesh" sandwich is compressed with a load and dried. This process produces a dried large area submucosal sheet that can be peeled off the mesh.

[0018] In one embodiment the submucosal tissue construct is formed from two or more strips of submucosal tissue pressed together and dried through the use of vacuum bagging. In that method submucosal tissue is laid out between two perforated, preferably stainless steel, plates. The plates are shaped to define the desired shape, *e.g.* a pouch construct, for the bladder replacement graft. The material is optionally placed on a surface and covered with blotting material to soak up water, and a breather blanket to allow air flow. The resulting "sandwich" of pressure plates and submucosal tissue is then sealed into a nylon bag that has a vacuum port. A vacuum is applied to pull air out of the vacuum bag and the resulting drop in atmospheric pressure compresses the plates against the submucosal tissue and simultaneously, at least partially, dehydrates the submucosal tissue. After 4 to 24 hours of applying a vacuum, the produced sheet is still moist and very flexible. No seams from the layering of the submucosal tissue are visible and the strength of a prototype 8-thickness sheet as determined by ball burst test is approximately 36.36 kg. (80 pounds). This general procedure can also be used to shape single submucosa tissue strips for use in this invention, if "shaping" of such single layer submucosa constructs is determined to be necessary or appropriate for particular surgical application.

[0019] Alternatively, large area sheets of submucosal tissue can be formed from smaller segments of submucosal tissue through the use of sutures and/or the use of binder pastes as described in U.S. Patent No. 3,562,820.

[0020] The mechanical properties of the large area submucosal sheet can be altered by adjusting the number of layers in the sheet, varying the angle of adjacent layers to each other, and varying the load applied to press the submucosal strips into a large area submucosal sheet.

[0021] The submucosal tissue grafts of the present invention can be preconditioned by stretching the material in a longitudinal or lateral direction as described in U.S. Patent No. 5,275,826. The submucosal material can be stretched prior to the formation of the graft constructs or during the formation of the constructs, or the submucos-

5

EP 0 820 301 B1

6

al tissue can be stretched after formation of the sheets.

[0022] The graft compositions of the present invention can be sterilized using conventional sterilization techniques including glutaraldehyde tanning, formaldehyde tanning at acidic pH, ethylene oxide treatment, propylene oxide treatment, gas plasma sterilization, gamma radiation, electron beam and peracetic acid sterilization. Sterilization techniques which do not adversely affect the mechanical strength, structure, and biotropic properties of the submucosal tissue is preferred. For instance, strong gamma radiation may cause loss of strength of the sheets of submucosal tissue. Preferred sterilization techniques include exposing the graft to peracetic acid, 1-4 Mrads gamma irradiation (more preferably 1-2.5 Mrads of gamma irradiation) or gas plasma sterilization; peracetic acid sterilization is the most preferred sterilization method. Typically, the submucosal tissue is subjected to two or more sterilization processes. After the submucosal tissue is sterilized, for example by chemical treatment, the tissue may be wrapped in a plastic or foil wrap and sterilized again using electron beam or gamma irradiation sterilization techniques.

[0023] Tissue graft according to the present invention is used for replacing/reconstructing damaged or diseased urothelial tissue of the urinary tract. Urothelial tissue is defined herein as including the cells and tissues of the ureter, urethra and renal collection system. The submucosal graft constructs promote the growth of endogenous urothelial tissues upon implantation into a host organism. These graft constructs can be used to replace large sections of the ureter, urethra and urinary bladder.

[0024] Submucosal tissue graft constructs according to the present invention are to be surgically implanted to promote the growth of endogenous urinary bladder tissues having a urine impermeable cell layer and a functional muscle cell layer. The tissue graft material serves as a scaffold and induces the proliferation of functional urinary bladder tissue formation which replaces the tissue, graft without shrinkage of the graft area or formation of "scar" tissue.

[0025] As mentioned above, the tissue graft construct is formed in the shape of a pouch to assist in the replacement of large portions (i.e., greater than 20%) of the urinary bladder. The construct can be formed by surgical construction from one or more submucosal strips or by a compression-forming procedure such as that described above. Furthermore the tissue graft construct can be manipulated to form ports in the tissue graft for surgical attachment and fluid communication with the ureters and the urethra.

[0026] The tissue graft constructs of the present invention are to be implanted into a vertebrate host species to repair a damaged, diseased or otherwise functionally compromised urinary bladder. In one example the defective portion of the bladder is to be surgically removed and replaced with a tissue graft construct comprising submucosal tissue of a warm-blooded verte-

brate. Where the submucosal tissue is of intestinal origin it is preferred that the luminal side of the intestinal submucosal tissue is directed toward the bladder lumen. Large portions of the bladder can be removed and replaced with the tissue grafts of the present invention. After implantation, the constructs are eventually remodelled by the host with functional urinary bladder tissues having a stratification of cell layers similar to that found in the normal urinary bladder wall. It is anticipated that the entire urinary bladder can be replaced with the present graft construct to regenerate a functional urinary bladder.

[0027] *In vivo* experiments have been conducted in pigs, dogs and rats to investigate the efficacy of submucosal tissue as an augmentation cystoplasty graft (see examples 2, 3 and 4). These experiments confirm the efficacy of the present graft constructs for urinary bladder reconstruction. Morphologic examination of the urinary bladders from those experiments show that there was a clear remodeling of the tissue with minimal or no adhesions to the surrounding abdominal structures. Additionally, a smooth transitional epithelial cell layer was formed on the luminal surface creating a urine impermeable layer that retains urine.

[0028] The present experiments demonstrate that at least 70% of the original urinary bladder tissue can be removed and remodeled using the submucosal tissue grafts of the present invention. Thus only a small portion of the original urinary bladder tissue is required to be left while remodelling occurs. The source of the cells forming the smooth muscle cells of the urinary bladder has not been determined but likely represents mobilization of cells from the surrounding smooth muscle of the remaining urinary bladder, as well as circulating mononuclear cells that arrive at the site via the blood stream and differentiate into smooth muscle cells.

[0029] Histological data obtained from the rat bladder replacement studies revealed that transitional epithelium completely covered the submucosal tissue patch graft by two weeks post operative. Significant acute inflammatory response did not occur at any time during host remodeling. Host remodeling occurred primarily from mononuclear and fibroblastic cellular invasion from the periphery (2 weeks) which migrated toward the center (4 weeks) of the graft and was eventually replaced completely by native host tissue 3 months after implantation. Smooth muscle fibers, although sparse, were present at 4 weeks, and became fully organized and indistinguishable from normal bladder smooth muscle fibers at 11 months. Histologically, these findings imply that the cellular reaction represents a fibrovascular healing type reaction, and the mononuclear cellular infiltrate represented digestion of the submucosal collagen and its replacement by native collagen.

[0030] One complication associated with the use of foreign material in the urinary tract is the formation of calculi (the formation of inorganic masses, i.e., mineral salts or "kidney stones"). Although calculi were present

7

EP 0 820 301 B1

8

in a majority of the animals harvested after 3 months, they were free floating and not adherent to graft. Because stone analysis revealed hydroxyapatite and not struvite, an infectious cause for the calculi is reduced. A review of the previously published long term augmentation studies in rats also revealed bladder calculi present in their control group, gastrocystoplasty group, ileocystoplasty group, and colcystoplasty group. Bladder stone formation also been reported in a group of rats that received autoaugmentation. Therefore, it appears that any sort of bladder surgery in the rat predisposes it to stone formation. Given these findings, it appears that the calculi formation was due to the bladder surgery and not directly related to the submucosal graft material itself.

### Example 1

#### Preparation of submucosal tissue

[0031] Small intestine submucosa was prepared in accordance with the procedures described in U.S. Patent No. 4,902,508. Briefly, sections of porcine jejunum were harvested within ten minutes of euthanasia and immediately placed in 0.9% saline solution. These sections were cut into 10 to 20 cm lengths and the mesenteric tissues were removed from the segment of the small intestine. The small intestine was everted (inside out) and the tunica mucosa mechanically removed. The small intestinal segment was everted again (i.e., the stratum compactum on the luminal side, as in the original orientation) and the serosa and tunica muscularis were removed from the outer surface. The tissue was rinsed in saline and placed in a 10% neomycin sulfate solution until used as a graft material. Storage time for the graft material ranged from 2 weeks to 3 months. It should be noted that preparation of submucosal tissue is a mechanical process similar to that of sausage casing and involves no enzymatic reaction steps.

### Example 2

#### Surgical Repair of Rat Urinary Bladder

[0032] Twenty-two male Sprague Dawley rats, weighing between 250 and 300 mg., were anesthetized with nembutal (15 mg/kg) and a midline abdominal incision was made exposing the bladder. The thin attachments of the perivesical fat were sharply freed from the bladder exposing the bladder neck. Four suspensory sutures of 5-0 silk were then placed at the four corners of the bladder for ease of bladder manipulation. Utilizing microscissors, the entire dorsal surface of the bladder (10 mm x 10 mm) was excised (approximately one-third of the bladder surface area) and hemostasis obtained with microcautery. A piece of submucosal tissue graft was then fashioned slightly larger than the defect (stratum compactum surface facing the bladder lumen) and sewn into

place with 7-0 mild chromic using a continuous, non-interlocking suture. To ensure a competent closure, a dilute methylene blue solution was injected through a 30 gauge needle on the ventral surface of the bladder. Sutured margins from which dye extravasated were oversewn with interrupted 7-0 mild chromic sutures. The submucosal tissue graft borders were then marked with four permanent marking sutures (proline) for future reference as to the exact position of the graft. The abdominal wounds were then closed in two layers with running 5-0 Dexon for both the muscle and skin. Urinary diversion or drains were not used in the immediate postoperative period nor did any of the animals receive antibiotics during the study period.

[0033] For histologic evaluation, animals were sacrificed at 2, 4, 8, 12, 24, and 48 weeks post-augmentation and the resected bladders were fixed in buffered 10% formalin solution for at least 24 hours. After fixation, each specimen was bisected in a sagittal plane through the trigone and the grafted region at the dome of the bladder. Both halves were embedded in paraffin. Sections were cut at 5 microns and stained with Massons hematoxylin and eosin, Periodic acid-Schiff, and Massons trichrome stains.

#### Results

[0034] Macroscopically, the inflated bladder specimens were uniformly dilated without evidence of diverticular formation in the region of the graft. The grafts were barely discernible as a slightly whitened area compared to the surrounding native bladder. There were minimal adhesions to the surrounding perivesical fat or other intraabdominal structures. Free floating, tan-brown calculi non-adherent to the graft were noted in the bladders of three of the four animals harvested at twelve weeks, one of two animals harvested at twenty-four weeks, and three of four of the animals harvested at forty-eight weeks. None of the other animals had any evidence of bladder calculi. Routine stone analysis revealed 100% hydroxyapatite. No gross evidence of hydronephrosis was apparent in any of the animals. Two animals died in the early postoperative period secondary to suture line leakage and these animals were replaced to maintain the total number of animals at 22. No other animals were lost throughout the study period.

[0035] Histologically, at two weeks, the submucosal tissue grafts were completely covered by transitional epithelium. Grafts showed a prominent vascular proliferation (neovascularization) at their edges and infiltration of their entire surface by fibroblasts and new capillaries. There was a moderately intense mononuclear inflammatory cell response in the periphery. Centrally, the inflammation was less intense, and fibroblasts and small capillaries infiltrated the collagen fibers of the submucosal tissue.

[0036] By four weeks, the grafts were infiltrated com-

9

EP 0 820 301 B1

10

pletely by well-formed small blood vessels and fibroblasts. Mononuclear inflammatory cell infiltrates were minimal at the edges but moderately intense in the central region. Myofibers with morphologic and staining characteristics consistent with smooth muscle were scattered throughout the periphery.

[0037] At three months, inflammatory activity throughout the graft had subsided, and small but well-formed blood vessels persisted. Collagen was well organized, and scattered fibroblasts were interspersed among the individual collagen fibers. Small myofibers with morphologic and staining properties of smooth muscle were present scattered throughout. In addition, distinct bundles of well-formed smooth muscle now were evident in a small portions of the grafts.

[0038] Finally, at 24 and 48 weeks post-augmentation all three layers of the normal rat bladder (urothelium, smooth muscle and serosa) were present and grossly and microscopically indistinguishable from the normal rat bladder. The permanent marking sutures delineating the margins of the submucosal tissue graft were the only guide to where the submucosal tissue graft had been surgically implanted and there was no evidence of graft shrinkage. Animals with bladder calculi present had a global urothelial inflammation in both the submucosal tissue regenerated and remaining normal bladder. Animals without calculi had no signs of inflammation.

### Example 3

#### Surgical Repair of Dog Urinary Bladder

[0039] A dog study comprising fourteen animals was also conducted in which 30-70% of the urinary bladder was replaced by peracetic acid sterilized submucosal tissue material. The animals were sacrificed at 1 week, 2 weeks, 4 weeks, 8 weeks, 12 weeks, 6 months, and 14 months after surgery. In summary, the animals all showed the ability to retain urine, and to urinate normally, within two days of the surgery. The urinary bladders remodeled (the graft tissue was replaced with endogenous urinary bladder tissue) within a very short period of time (1-2 weeks) to contain a normal transitional epithelium, basement membrane, submucosa, and a thinner and normal but definitely organized smooth muscle cell layer. None of the dogs became infected, showed fever, or showed any evidence of rejection of the xenogeneic material.

[0040] *In vitro* studies of the excised tissue at the time of sacrifice show that the newly remodeled urinary bladder contained contractile and functioning spindle cells (smooth muscle cells) and had neural receptors. These cells reacted in response to carbachol and to nicotine. The carbachol responses were blocked by atropine. Additionally, the smooth muscle cells responded to electrical stimulus at approximately 75% of the normal urinary bladder smooth muscle contractile force.

[0041] The volume of the urinary bladder prior to sur-

gery was approximately 51 mls and at the time of sacrifice the urinary bladder volume was approximately 55 mls. Thus the size of the urinary bladder was retained with the use of the submucosal tissue graft material and there was no evidence of shrinkage as would be expected in "scarring".

[0042] The ability of the reconstructed urinary bladder to exert pressure was maintained. The pressure producing capabilities of the urine were 52 cm of water prior to surgery and 45 cm of water at the time of sacrifice.

### Claims

1. A tissue graft construct for replacement of damaged or diseased portions of a urinary bladder, said construct comprising a sheet of submucosal tissue of a warm-blooded vertebrate formed in the shape of a urinary bladder for replacing 20% or more of the urinary bladder.
2. The tissue graft construct of claim 1 wherein said tissue graft construct has ports for surgical attachment and fluid communication with the ureters and the urethra.
3. The tissue graft construct of claim 1 wherein said tissue graft construct is formed from two or more strips of submucosal tissue of a warm-blooded vertebrate, said graft construct having a surface area greater than any one of the individual strips used to form said graft construct.
4. The tissue graft construct of claim 1, wherein the submucosal tissue is intestinal submucosa comprising the tunica submucosa delaminated from both the tunica muscularis and the luminal portion of the tunica mucosa.
5. A tissue graft construct for replacement of damaged or diseased portions of a urinary bladder, said construct comprising a sheet of submucosal tissue of a warm-blooded vertebrate formed as a pouch for replacement of 20% or more of the urinary bladder.
6. The tissue graft construct of claim 5 wherein said pouch has ports for surgical attachment and fluid communication with the ureters and the urethra.
7. The tissue graft construct of claim 5 wherein said tissue graft construct is formed from two or more strips of submucosal tissue of a warm-blooded vertebrate, said graft construct having a surface area greater than any of the individual strips used to form said graft construct.
8. The tissue graft construct of claim 5 wherein the submucosal tissue is intestinal submucosa com-

11

EP 0 820 301 B1

12

prising the tunica submucosa delaminated from both the tunica muscularis and the luminal portion of the tunica mucosa.

weist, der größer als jeder der einzelnen zur Bildung des Transplantatkonstrukts verwendeten Streifen ist.

#### Patentansprüche

1. Gewebetransplantatkonstrukt zur Ersetzung von beschädigten oder kranken Bereichen einer Harnblase, **dadurch gekennzeichnet, dass** das Konstrukt eine Lage von submucosalem Gewebe aus einem warmblütigen Wirbeltier aufweist, die in der Gestalt einer Harnblase zum Ersatz von 20% oder mehr der Harnblase geformt ist.
2. Gewebetransplantatkonstrukt nach Anspruch 1, **dadurch gekennzeichnet, dass** das Gewebetransplantatkonstrukt Öffnungen zur chirurgischen Anbringung und fluiden Kommunikation mit den Harnleitern und der Harnröhre aufweist.
3. Gewebetransplantatkonstrukt nach Anspruch 1, **dadurch gekennzeichnet, dass** das Gewebetransplantatkonstrukt aus zwei oder mehreren Streifen von submucosalem Gewebe eines warmblütigen Wirbeltieres ausgebildet ist und dass das Transplantatkonstrukt einen oberflächlichen Bereich aufweist, der größer ist als jeder der einzelnen zur Bildung des Transplantatkonstrukts verwendeten Streifen.
4. Gewebetransplantatkonstrukt nach Anspruch 1, **dadurch gekennzeichnet, dass** das submucosale Gewebe Darmsubmucosa ist, die sowohl von der Tunica muscularis und dem luminalen Bereich der Tunica mucosa delaminierte Tunica submucosa aufweist.
5. Gewebetransplantatkonstrukt zum Ersatz von beschädigten oder kranken Bereichen einer Harnblase, **dadurch gekennzeichnet, dass** das Konstrukt eine Lage von submucosalem Gewebe eines warmblütigen Wirbeltieres aufweist, die als eine Tasche zum Ersatz von 20% oder mehr der Harnblase geformt ist.
6. Gewebetransplantatkonstrukt nach Anspruch 5, **dadurch gekennzeichnet, dass** die Tasche Öffnungen zur chirurgischen Anbringung und fluiden Kommunikation mit den Harnleitern und mit der Harnröhre aufweist.
7. Gewebetransplantatkonstrukt nach Anspruch 5, **dadurch gekennzeichnet, dass** das Gewebetransplantatkonstrukt aus zwei oder mehr Streifen von submucosalem Gewebe eines warmblütigen Wirbeltieres ausgebildet ist und dass das Transplantatkonstrukt einen Oberflächenbereich auf-

- 5 8. Gewebetransplantatkonstrukt nach Anspruch 5, **dadurch gekennzeichnet, dass** das submucosale Gewebe Darmsubmucosa ist, die sowohl von der Tunica muscularis und dem luminalen Bereich der Tunica mucosa delaminierte Tunica submucosa ist.

#### Revendications

- 15 1. Structure pour greffe de tissu destinée à remplacer des parties endommagées ou malades d'une vessie, ladite structure comprenant une feuille de tissu sous-muqueux d'un vertébré à sang chaud configurée sous la forme d'une vessie afin de remplacer 20 % ou plus de la vessie.
- 20 2. Structure pour greffe de tissu selon la revendication 1, dans laquelle ladite structure pour greffe de tissu présente des orifices à des fins de fixation chirurgicale et de communication fluide avec les uretères et l'urètre.
- 25 3. Structure pour greffe de tissu selon la revendication 1, dans laquelle ladite structure pour greffe de tissu est formée de deux bandes ou plus de tissu sous-muqueux d'un vertébré à sang chaud, ladite structure pour greffe de tissu ayant une surface supérieure à n'importe laquelle des bandes individuelles utilisées pour former ladite structure pour greffe.
- 30 4. Structure pour greffe de tissu selon la revendication 1, dans laquelle le tissu sous-muqueux est la sous-muqueuse intestinale comprenant la sous-muqueuse décollée à la fois de la tunique musculaire et de la partie luminale de la muqueuse.
- 35 5. Structure pour greffe de tissu destinée à remplacer des parties endommagées ou malades d'une vessie, ladite structure comprenant une feuille de tissu sous-muqueux d'un vertébré à sang chaud configurée sous forme de poche afin de remplacer 20 % ou plus de la vessie.
- 40 6. Structure pour greffe de tissu selon la revendication 5, dans laquelle ladite poche présente des orifices à des fins de fixation chirurgicale et de communication fluide avec les uretères et l'urètre.
- 45 7. Structure pour greffe de tissu selon la revendication 5, dans laquelle ladite structure pour greffe de tissu est formée à partir de deux bandes ou plus de tissu sous-muqueux d'un vertébré à sang chaud, ladite structure pour greffe de tissu ayant une surface supérieure à n'importe laquelle des bandes individuel-
- 50
- 55

13

EP 0 820 301 B1

14

les utilisées pour former ladite structure pour greffe.

8. Structure pour greffe de tissu selon la revendication 5, dans laquelle le tissu sous-muqueux est la sous-muqueuse intestinale comprenant la sous-muqueuse décollée à la fois de la tunique musculaire et de la partie luminale de la muqueuse.

10

15

20

25

30

35

40

45

50

55